

H100

Water activated semi-flexible polyurethane foam injection resin.

Description One component, closed cell, hydrophobic, water reactive, solvent and phthalate free, low viscosity polyurethane injection resin for stabilization and water cut-off of large water leaks.

- Applications**
- Water cut-off of large flow and high pressure water leaks.
 - Water cut-off of water leaks in foundations such as diaphragm walls, piling sheets and secant piles.
 - Stabilization and water cut-off of large cracks, voids and gravel layers.
 - Pre and post injections in mines, tunnels, pipe jacking, drill & blast and TBM applications.
 - Injections in combination with cement-based grout.
 - Crack and gravel layer injections in concrete structures.
 - Soil stabilization and anchors in porous geology.
 - Water cut-off of sewer water leaks and sewer stabilization.
 - Probe grouting for below grade pipes.
 - Manhole injections.

- Advantages**
- One component.
 - Different reaction times are possible by adjusting the percentage of H100 ACC accelerator.
 - The closed-cell structure of cured polyurethane ensures permanent sealing of cracks and joints.
 - Cured polyurethane exhibits high strength and good chemical resistance (contact our Technical Service for chemical resistance).
 - Cured polyurethane is harmless for the environment and resistant to biological attack.
 - WQA drinking water certificate.

Packaging 5 Gallon Pails



C US

Spetec PU H100 when combined with the ACC H100 accelerator is certified by WQA to NSF/ANSI 61 and CSA-B483.1 for materials safety only, as verified and substantiated by test data. Please refer to WQA website (www.wqa.org) for more information.

Properties

Uncured

(appearance brown liquid)

Viscosity at 77°F	(ASTM D4878-98)	±160cps
Flash Point	(ASTM D1310-86)	>302°F
Density	(ASTM D3505-96 [2000])	1.058 ± 0.005

Cured

Compressive strength	942psi
Tensile strength	290psi
Flexural strength	>10MPa
Density	EN ISO 1183 62.43lb/ft3

Reaction Rate with ACC H100 Accelerator

%	41°F		59°F		77°F		Expansion
	Start	End	Start	End	Start	End	
2	55"	300"	42"	170"	35"	110"	15V
6	35"	85"	32"	80"	25"	75"	17V
10	25"	65"	22"	60"	18"	50"	18V

Material Prep	Condition overnight to 70° - 80° F (21° - 26° C). Heat bands or hot water bath may be used to warm containers. Do not heat above 80 degrees F.
Mixing	Vigorously shake the H100 ACC accelerator before use and broadcast the required quantity (2-10%) into the PU H100 resin. Mix the accelerator homogeneously into the resin and protect against moisture and rain to prevent premature reaction.
Equipment	Depending on the application, injection can be carried out using a hand pump, pneumatic pump or electric pump. Preferably use a separate pump for injection of water and resin.
Accessories	ACC H100 Accelerator, AP Flush 121, AP Soak 130
Personal Protection	Safety goggles, face shield, impermeable gloves, long sleeves and pants. Use in well ventilated areas. Open doors and windows. In confined areas use mechanical ventilation to keep vapor concentrations low. Prevent direct contact with skin and eyes. See SDS.
Clean Up	Flush injection equipment with AP Flush 121 when necessary. Remove cured material from metal components by soaking in AP Soak 130. Clean off of skin with soap and water.
Environmental Protection	Cured material is chemically inert and safe to dispose of in landfill. Cleanup any spilled liquid resin and place in a suitable sealed container. Dispose of in accordance to applicable environmental regulations.
First Aid	Eye Contact: Immediately flush with large amounts of water. Seek medical attention. Inhalation: Move to fresh air if symptoms occur. If breathing is difficult, seek medical attention. Ingestion: Seek medical attention immediately. Skin Contact: Wipe off contaminated area and wash with soap and water.
Limitations	Low temperatures will increase viscosity making product more difficult to pump. Low temperatures or cold water will slow down the reaction time. pH of reaction water should be between 3 and 10 for optimum foam. Keep lid tightly closed.
Storage	Store between 50° - 85° F (10° - 29° C).
Handling	Keep lids on tightly to prevent moisture from entering containers. Avoid direct contact with product. Be careful when opening as pressure may build up inside containers.
Limited Warranty	Alchemy-Spetec warrants this product to be free from manufacturer's defects and to meet all published properties on current Technical Data Sheet for a period of one year if used according to published instructions and within the shelf life. The user is responsible for determining suitability for intended use and assumes all risk. No other warranties expressed or implied shall apply including any warranty of merchantability or fitness for a particular purpose. Purchaser's sole remedy is limited to the purchase price or product replacement exclusive of cost of labor or other materials.
Latest Information	Before each use read latest Technical Data Sheets, Safety Data Sheets, and instructions available at www.alchemypolymers.com . Nothing contained in any Alchemy-Spetec materials or verbal instruction relieves the user of the obligation to read and follow all usage instructions and warnings for each product contained in the latest Technical Data Sheets and Safety Data Sheets. All information given by Alchemy-Spetec about Alchemy-Spetec products and procedures is given in good faith based on our current experience level and knowledge when materials are properly stored, handled, and applied. Jobsite conditions always vary, and for this reason Alchemy-Spetec assumes no liability for the provision of such information or instructions. Neither shall any legal relationship be created by the provision of such information.

FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. READ MATERIAL SAFETY DATA SHEET PRIOR TO EVERY USE.

